



Systemabdichtungsbaustoffe

KAUBIT Aktiengesellschaft • Industriestraße 1 • 49413 Dinklage
Telephone: +49 4443 9669-0 • Telefax: +49 4443 9669-66 • Internet: www.kaubit.de • E-Mail: info@kaubit.de

Kaubit Primer UKD 200

Technical Data Sheet

01.12.2021

Solvent-free styrene / butadiene-based primer

Properties:

Solvent-free primer for use on absorbent and less absorbent substrates. Prevents quick dehydration of thin bed mortars and levelling compounds, prolongs open time, improves adhesion and prevents shrinkage cracking of covering layers.

Applications:

As bonding agent for use on all mineral cement-based substrates.

Technical specifications:

Application temperature: +5°C to +25°C
Colour: milky blue
Density: 1 g/cm³
pH: 9



Preparation of the substrate:

The substrate must be firm, level and stable and free of oil, grease, soiling and other substances which would impair adhesion. Fresh cement flooring may not have a residual moisture content exceeding 2% (measurement with CM instrument).

Use:

Stir well prior to use and apply evenly with a brush or swab. After the fumes have cleared, the covering layer can be applied.

Consumption:

Consumption is determined by the absorbency and nature of the substrate; required is 100 - 250 g/m².

Drying time:

Determined by temperature, humidity and the absorbency of the substrate: expect 2 hours at +20°C and 50% relative humidity.

Information on further processing:

The required products may be applied after the primer has dried.

Cleaning of tools and equipment:

Wash all tools and any soiled areas with water immediately after use.

Storage:

Can be stored in the original bottle / canister for up to 12 months in a cool and frost-free space.

Supplied as:

1 kg bottle	5 kg can
10 bottles / cartons	90 cans / pallet
48 cartons / pallet	
10 kg can	20 kg can
60 cans / pallet	24 cans / pallet

Further sizes available on request.

Safety information:

Not a hazardous substance according to the Ordinance on Hazardous Substances.

Disposal:

Can be disposed of as construction waste.

For further information see also Material Safety Data Sheet (MSDS).